

测量过程核查记录

测量过程名称:	产品绝缘护套厚度检测过程			测量过程编号:		JLY-02			记录流水号: 2022001			
测量参数:	绝缘护套厚度			测量最大允许误差:		±0.004mm			备注: 单位为mm			
核查标准:	标准样品			核查周期:		1月/次						
核查日期	1	2	3	4	5	6	7	8	9	10	平均值 ($\bar{x}$)	标准偏差 (s)
2022/1/3	0.722	0.721	0.723	0.721	0.723	0.721	0.722	0.723	0.721	0.722	0.722	0.0009
2022/3/10	0.715	0.716	0.717	0.714	0.715	0.716	0.716	0.715	0.716	0.716	0.716	0.0008
2022/4/1	0.733	0.735	0.735	0.734	0.734	0.733	0.735	0.734	0.733	0.733	0.734	0.0009
2022/5/3	0.713	0.713	0.714	0.715	0.714	0.713	0.714	0.715	0.713	0.715	0.714	0.0009
2022/6/1	0.713	0.712	0.713	0.711	0.713	0.712	0.712	0.712	0.713	0.713	0.712	0.0007
2022/7/1	0.711	0.710	0.712	0.710	0.712	0.711	0.710	0.711	0.711	0.712	0.711	0.0008
2022/8/1	0.723	0.722	0.722	0.721	0.723	0.722	0.722	0.723	0.721	0.722	0.722	0.0007
2022/9/1	0.734	0.733	0.733	0.732	0.733	0.734	0.732	0.733	0.732	0.733	0.733	0.0007
2022/10/3	0.713	0.713	0.713	0.712	0.713	0.712	0.712	0.711	0.713	0.713	0.713	0.0007
2022/11/1	0.731	0.732	0.733	0.731	0.733	0.732	0.733	0.732	0.733	0.732	0.732	0.0008
m = 6			n = 10									
平均值 ($\bar{x}$) = 0.72			sB = 0.010			s _p = 0.001						

$\bar{x}$ - s图

